See discussions, stats, and author profiles for this publication at: https://www.researchgate.net/publication/359523595

Investigation of Structural, Electronic and Optical Properties of SrTiO3 and SrTio.94Ago.06O3 Quantum Dots Based Semiconductor Using First Principle Approach

Article *in* Advanced Journal of Chemistry-Section A · March 2022 DOI:10.22034/AJCA.2022.325958.1300

CITATION 1		reads 40	
9 authors, including:			
	Jahedul Islam Presidency University 5 PUBLICATIONS 9 CITATIONS SEE PROFILE		Ajoy Kumer European University of Bangladesh 92 PUBLICATIONS 444 CITATIONS SEE PROFILE
and a second	Unesco Chakma European University of Bangladesh 37 PUBLICATIONS 139 CITATIONS SEE PROFILE		Md. Monsur Alam European University of Bangladesh 9 PUBLICATIONS 9 CITATIONS SEE PROFILE

Some of the authors of this publication are also working on these related projects:

Prediction the thermophysical properties, chemical reactivity, and biological study for Ionic Liquids, natural products, organomatallic crystal and dye. View project

First principle study for semiconductor, superconductor, photocatalyst and organo-metallic crystals View project



Advanced Journal of Chemistry-Section A Theoretical, Engineering and Applied Chemistry

Journal homepage: www.ajchem-a.com



Original Research Article

Investigation of Structural, Electronic and Optical Properties of SrTiO₃ and SrTi_{0.94}Ag_{0.06}O₃ Quantum Dots Based Semiconductor Using First Principle Approach

Jahedul Islam¹, Ajoy Kumer^{2,3} * ⁽¹⁾, Unesco Chakma⁴ * ⁽¹⁾, Md. Monsur Alam⁵, Shimul Biswas⁴, Zubair Ahmad⁴, Md Shariful Islam⁶, Ms Ismat Jahan jony², Md Boshir Ahmed⁷

¹ Department of Civil Engineering, Presidency University, Dhaka, Bangladesh

² Department of Chemistry, European University of Bangladesh, Gabtoli, Dhaka-1216, Bangladesh

³ Department of Chemistry, Bangladesh University of Engineering Technology, Dhaka-1000, Bangladesh

⁴ Department of Electrical and Electronics Engineering, European University of Bangladesh, Gabtoli, Dhaka-1216, Bangladesh

⁵ Department of Planning and Development, European University of Bangladesh, Gabtoli, Dhaka-1216, Bangladesh

⁶ Department of Civil Engineering, European University of Bangladesh, Gabtoli, Dhaka-1216, Bangladesh

⁷ Department of Chemistry, West Virginia University, WV 26506, Morgantown, United States

ARTICLE INFO

Article history

Submitted: 22 January 2022 Revised: 26 February 2022 Accepted: 18 March 2022 Available online: 23 March 2022 Manuscript ID: AJCA-2201-1300 Checked for Plagiarism: Yes

DOI: 10.22034/AJCA.2022.325958.1300

KEYWORDS

Band gap DOS Optical properties Doping and Density Functional Theory

ABSTRACT

Due to the legitimate crystal size of SrTiO₃, in this work, a synthesized compound was introduced and structurally characterized as the quantum dots. The crystal of SrTiO₃ was designed using computational tools. There is no obtainable information for hypothetical and conceptual studies, and computational studies. First, using the CASTAP code from material studio 8.0 the structural geometry was optimized using the generalized gradient approximation (GGA) with the hybrid functional, Perdew-Burke-Ernzerhof (PBE) to calculate the electronic structure, geometry, and optical properties for the SrTiO₃. The crystal size of the optimized structure was 2.0 nm for both SrTiO₃ and SrTi_{0.94}Ag_{0.06}O₃, which stays in quantum dots. With the help of GGA with PBE, the band gap was recorded at 1.77 eV, and for evaluating the nature of 5s, 4p, and 3d orbitals for a Sr atom, 4s, 3p and 3d orbitals for Ti atom, 5s, 4p, and 4d orbitals for Ag atom and 2s, and 2p orbitals for 0 atom for $SrTiO_3$ are obtained. Density of state(DOS) and the partial Density of state(PDOS) of SrTi0.94Ag0.0603 were replicated. The optical properties, like absorption, reflection, refractive index, and conductivity, were replicated, dielectric function and loss function was computed. By replacing the Ti atom on SrTiO₃ 6% Ag atom was doped to elaborate the demeanor nature, and because of this 0.00 eV band gap was obtained having a molecular formula by SrTi_{0.94}Ag_{0.06}O₃ , as well as the optical conductivity and optical absorption was soared compared with parent SrTiO₃.

* Corresponding author: Kumer, Ajoy; Chakma, Unesco E-mail: kumarajoy.cu@gmail.com; unescochakma@gmail.com © 2022 by SPC (Sami Publishing Company)



GRAPHICAL ABSTRACT

Introduction

During this digital era, a wide technological advancement in electronics is increasing, like the speed of light. This field of electronics is much more dependent on semiconductor materials because most of the applications used in these fields, such as IC, LCD/LED, BJT, MOSFET, transistor, resistor, photovoltaic solar powerare quite impossible to make without semiconductor materials [1-3]. It is also an essential fact that for the development of the national economy and national security, every country uses high-speed computing, large-capacity data communication, storage, processing, electronic devices, which also depend on a larger scale on semiconductors [4-6]. The conventional semiconductor materials used in electronics are changing every single second. For example, the quantum dots are replacing the conventional narrow and wide band gap semiconductor materials whose range is recorded by many researchers and scientists in between 1.8 to 4.0 eV [7,8]. Quantum dots are semiconductor particles having a few nanometer sizes. For example, SrTiO3, also known as strontium titanate, has less than 1.8 eV band gap and at room temperature and low electric field, a very large dielectric constant (300) [9,10]. Due to this a low band gap and a large dielectric constant value, it can store more charge, and that is why it has a wide range of uses, such as highvoltage capacitors, voltage-dependent resistors, optical instruments, jewelry stone, advanced ceramics, and substrates for superconductors [11,12].

However, the commercialization of DSSCs gets notably dragged due to the areal cost and bustling synthesis procedures of organic dyes and limited quantum efficiency. On the other hand, quantum dots (QDs) are considered excellent light harvesters to substitute organic dyes in these macroscopic solar cells due to their tunable band gaps, light-response ranges, scalable materials, and cost-effectiveness.

Narrow band gap semiconductors are a class of Quantum dots that have benefits like tunable band gaps due to the quantum confinement result [13], higher absorption coefficients than most organic dyes [14,15], and various exactions generation have more [16,17]. For macroscopic solar cells QDs have been analyzed to serve as light absorbers, such as CdS, CdSe, PbS, PbSe and integrated CdS/CdSe, CdS/PbS, CuInS₂/CdS, CuInS₂/In₂S₃, CdSe/CdTe, CdSe/GO, etc [18], inverter [5], Double Perovskites [19,20]. However, these materials are always restricted due to their intrinsic band gaps. Due to negligible toxicity, easy formulation, scalable materials, and performances, a class of lead-free perovskitestructured Quantum Dots has been highlighted nowadays [21,22]. The reduction of band gap using the doping process can make SrTiO₃ more efficient quantum dots, and this investigation is based on the same principle.

In this investigation, the band gap was determined using computational tools, which supports less time and cost than experiments and compares the calculated band gap to the experiment value for its validation [23-30]. Additionally, to develop and enhance its activity, Ag was doped on $SrTiO_3$ because Ag increases electron density, doping power, and decreases band gap by overlapping with the orbital of the materials and enhances quantum dots efficiency [24,31-34].

As quantum dots, there are not enormous studies on $SrTi_{0.94}Ag_{0.06}O_3$. For this view, the main goal of this study is to investigate the effect of Agdoped replacing Ti atom on the SrTiO₃ compound, and its molecular formula becomes SrTi_{0.94}Ag_{0.06}O₃ after 6% Ag doping. As a result, these properties, which have been derived from simulation after doping, have significant intensive attention for potential applications. For using the SrTiO₃, this study supports to development of the theoretical concept using the first principle study and opens a new window for potential application by Ag doping in SrTiO₃.

Computational Methods

With instigating, before energy calculation, the geometrical optimization was acquired where the convergence criterion for the force between atoms was 3×10^{-6} eV/A°, and the maximum displacement, the total energy, and the maximal stress were at 1×10^{-3} A°, 1×10^{-5} eV/atom and 5×10^{-2} GPa, respectively. After geometrical stability of the configuration, using the GGA with PBE functional from CASTEP code of the material studio version 8.0, the electronic band structure, the total density of state (TDOS), and partial density of state (PDOS) were computed [35].

The main reason is the most viable and acceptable method for computing the electronic structure and optical properties [31-33, 36, 37]. Using this condition and keeping the cut off at 500 eV, and k point at $2 \times 2 \times 2$ with norm-conserving pseudopotentials, the band structure, density of state, and Generalized Gradient Approximation (GGA) with Perdew-Burke-Ernzerhof (PBE) [38] functional of SrTiO₃ and SrTi_{0.94}Ag_{0.06}O₃ for the comparative study of band gaps were calculated and after that the optical properties like refractive index, reflectivity, absorption, conductivity, and loss function, were similarly simulated for computation.

Results and Discussions

Geometry of optimized structure

The lattice parameters value was computed for the crystals after the geometry optimization. Here, a = 5.629 Å, b = 5.629 Å and c = 13.886 Å while angles among them as α = 90.00°, β = 90.00° , and γ = 120.00° It is a monoclinic SrTiO₃ crystal, and the space group is Hermanna Mauguin P63/mmc [194], triclinic crystal system, point group 6/mmm, hall-P 6c 2c, density 4.80 g/cm³ shown in Figure 1a. The Ag atom doping in optimized structures are accounted for in Figure 1b.



Figure 1a. Structure for SrTiO₃

Electronic band structure

The Fermi energy level is situated at zero energy level to determine the electronic band structure of $SrTiO_3$ and $SrTi_{0.94}Ag_{0.06}O_3$. From Figure 2a for $SrTiO_3$ quantum dots, the minimum of conduction (MCB) is obtained at the G symmetry point, whereas the maximum of valance bands (MVB) is also found at G symmetry points. A direct band gap is calculated with a value of 1.77 eV. The main key point of this research was noted that the band gap of $SrTiO_3$







Figure 1b. Structure for SrTi 0.94Ag0.06O3

has been reduced, and it becomes more effective quantum dots when the Ag has doped by 6%. The reason is that Ag atom can enhance the electron density in both areas of valance band and conduction band besides d and p orbitals of Ag atom have quickly overlapped with the p and d orbitals with Sr and Ti metals for quickly transferring the hole electrons. That is why the minimum portion of Ag by 6% was doped in SrTiO₃ and illustrated the effect on the band structure. The band gap was recorded at the G sy-



Figure 2b.Electronic structure for SrTi_{0.94}Ag_{0.06}O₃

-mmetry point for both MCB and MVB after doping, showing a direct band gap by 0.00 eV, which stands for that Ag atom has a high capacity on $SrTiO_3$ to reduce the band gap and make it more efficient quantum dots.

The Density of states (DOS) and Partial density of state (PDOS)

The splitting of an orbital and the position of the electronic band structures are designated by a parameter known as the DOS. For calculating the



Figure 3a.Total density of states for $SrTiO_3$ and $SrTi_{0.94}Ag_{0.06}O_3$



Figure 3c. Partial Total density of states for $SrTi_{0.94}Ag_{0.06}O_3$

DOS of Sr, Ti, Ag, and O atoms for SrTiO₃ and SrTi_{0.94}Ag_{0.06}O₃ crystals, the GGA with PBE method was executed. From the Figure 3b to 3c, the sum of DOS for SrTiO₃ and SrTi_{0.94}Ag_{0.06}O₃ crystals consists of 5s, 4p, and 3d orbitals for a Sr atom, 4s, 3p and 3d orbitals for Ti atom, and 5s, 4p, and 4d orbitals for Ag atom and 2s and 2p orbitals for O atom. Figure 3d to Figure 3f demonstrated that comparison s, p and d orbitals for SrTiO₃ and SrTi_{0.94}Ag_{0.06}O₃ and the comparison study focus that s, p, and d orbital of SrTi_{0.94}Ag_{0.06}O₃ higher than SrTiO₃.



Figure 3b. Partial Total density of states for $SrTiO_3$



Figure 3d. Comparison s orbital for $SrTiO_3$ and $SrTi_{0.94}Ag_{0.06}O_3$



Figure 3e. Comparison p orbital for $SrTiO_3$ and $SrTi_{0.94}Ag_{0.06}O_3$

Secondly, the DOS of $SrTi_{0.94}Ag_{0.06}O_3$ in the conduction band is almost more significant than the DOS of $SrTiO_3$ at 0.2 eV to 2.5 eV. The DOS of the valance band is found at -0.1 to -5.0 electron/eV, while the DOS of the conduction band is recorded at about 30 electron/eV. To compare the s, p, and d orbitals for both doping and undoped, the orbitals for $SrTi_{0.94}Ag_{0.06}O_3$ are much higher than $SrTiO_3$, and it can be said that the Ag doping on $SrTiO_3$ has increased the DOS of any crystal showing in figures 3a, 3b, 3c, 3d, 3e, and 3f.

Optical Properties



Figure 4. Reflectivity



Figure 3f. Comparison d orbital for $SrTiO_3$ and $SrTi_{0.94}Ag_{0.06}O_3$

Reflectivity

Reflectivity is the measurement of reflected light from the surface area of the material relative to the amount of light incident on the material. In this investigation, the reflectivity of $SrTiO_3$ and $SrTi_{0.94}Ag_{0.06}O_3$ is demonstrated in Figure 04. The initial reflectivity of $SrTiO_3$ was recorded at 0.17, and with the increase of energy, it increases. Less reflectivity means more efficient quantum dots. After doping Ag, the initial reflectivity was recorded at 0.27, which decreased with the increase of energy and proved $SrTi_{0.94}Ag_{0.06}O_3$ more efficient quantum dots.



Figure 5. Absorption

Absorption

The absorption spectrum of a material depends on the nature of the energy band gap, which pursues the indirect band gap usually absorbs more temperature than the direct band gap semiconductor. The absorption spectrum of $SrTi_{0.94}Ag_{0.06}O_3$ is less than $SrTiO_3$. With the increase of energy, the absorption of both materials $SrTiO_3$ and $SrTi_{0.94}Ag_{0.06}O_3$ increases. However, the $SrTi_{0.94}Ag_{0.06}O_3$ revealed a better value of absorption than $SrTiO_3$, as demonstrated in Figure 5.

Refractive Index

The optical and electronic properties of a material depend on physical parameters like



Figure 6. Refractive Index

Dielectric Function

The dielectric functions are calculated in the linear optical response regime within the electric dipole approximation. The required momentum matrix elements are obtained by using the calculated wave functions from our empirical pseudo potentials. Dielectric functions that describe the materials at the Nanoscale are needed, opening the way to interpret experimental data and design of the composites to obtain desired optical behavior. Despite the great interest in the research on NPs, there is

refractive index and energy band gap. These properties describe the nature of the applications of semiconductors, electronic, optical, and optoelectronic devices. The band gap engineered structures for continuous and optimal absorption of broad band spectral sources are also dependent on these properties. The real part and imaginary part of the refractive index of the SrTiO₃ and SrTi_{0.94}Ag_{0.06}O₃ are shown in Figure 6, which is an inverse pattern.

The refractive index is higher for a real part at the primary point of photon energy at that time, the imaginary part showed a value almost close to 1 eV. Afterwards, they follow a constant pattern with slightly different refractive index values. It is the same for both undoped and doped.



Figure 7. Dielectric Function

presently no available information about the dielectric functions of nano-sized semiconductors that could be readily used for macroscopic modeling applications. The dielectric function is an essential tool to investigate their optical properties, which is related to adsorption properties as the following equation for solid.

$$\varepsilon = \varepsilon_1(\omega) + i\varepsilon_2(\omega)$$

Here, ε_1 (ω), and ε_1 (ω) denotes the dielectric constant (real part) and the dielectric loss factor (imaginary part). The probability of photon

absorption for the band structure of any material is closely related to the imaginary portion of the dielectric function. The real part of the dielectric constant maintained the energy storage potential in the electric field, while the imaginary segment indicates the opposite even for electric potential energy. From Figure 7, the actual portion is always higher than the imaginary part within the energy at 1.0 eV to 1.8 eV, but the energy range from 2 eV to 4 eV. The imaginary part shows a higher value than real portion for SrTiO₃ and SrTi_{0.94}Ag_{0.06}O₃.

Conductivity

The conductivity can be explained in terms of band gap. The electronic conduction is nothing but putting an electron in the conduction band by giving enough energy to electron and shining the material with light. This process can be accomplished. In a solid-state language, by



Figure 8. Conductivity

Loss function

The loss function is a crucial part of optical properties, which is composed of two regions of photon energy parts such as the lower photon energy part and higher photon energy part for crystal materials. The energy loss function is closely related to the dielectric function of the creating a hole in the valence band the electron can go to conduction band with the help of photon energy. After that, an electrical conduction will occur due to free electrons and holes.

Figure 8 depicts the comparative study of the conductivity value of SrTiO₃ and SrTi_{0.94}Ag_{0.06}O₃ crystals. The conductivity values of both real and imaginary parts start from almost zero at 0.0 eV. The real part of conductivity increased with a similar trend for SrTiO₃ and SrTi_{0.94}Ag_{0.06}O₃ in the energy range from 0 eV to 5 eV and reached conductivity real peaked value 2.8 and 3.0. However, the conductivity value of SrTi_{0.94}Ag_{0.06}O₃ within energy range 1 to3 eV is higher than $SrTiO_3$. On the other hand, the part imaginary values of SrTiO₃ and SrTi_{0.94}Ag_{0.06}O₃ declined gradually after Fermi energy in the energy range from 3 eV and reached conductivity imaginary peaked values-2.1 and -2.5.



Figure 9. Loss Function

photocatalyst materials within the range of the dielectric theory validation. In the energy loss, function dielectric function reflects the response of a semiconductor to an external electromagnetic perturbation. The calculated exploration of loss function values for $SrTiO_3$ and $SrTi_{0.94}Ag_{0.06}O_3$ illustrates in figure 9. It can be

seen that the loss function of $SrTi_{0.94}Ag_{0.06}O_3$ is higher than $SrTi_{0.94}Ag_{0.06}O_3.$

Conclusion

To sum up, the electronic, structural, and optical properties of hexagonal SrTiO₃ and dots based SrTi_{0.94}Ag_{0.06}O₃ quantum semiconductor was studied for the first time using the Density functional theory (DFT) by the first principle approach. First of all, the band gap of SrTiO₃ has been recorded by 1.77 eV as supporting a semiconductor that has been filled up the lack of literacy about band gap and electronic structure for SrTiO₃ of a theoretical result. The superior outcome of this study was obtained by Ag atom doping effect on electronic structure, especially band gap, DOS, PDOS, and optical properties. After Ag doping by 6% in SrTiO₃, the band gap has shifted to 0.00 eV, acting as no resistance materials for optoelectronic devices, which has justified the PDOS and DOS diagram for delocalization of electrons. Secondly, the optical properties due to Ag doping have changed. The optical absorption, reflectivity, loss function, and conductivity of doped SrTiO₃ are greater than undoped SrTiO₃, but the real part of the dielectric function is lower than undoped. Finally, it can be said that the 6% Ag doping in SrTiO₃ is almost acted as a superconductor for a wide band gap QDs materials.

Acknowledgment

I am thankful to Prof. Md. Wahab Khan, and Prof. Al-Nakib Chawdhury, Department of Chemistry, Bangladesh University of Engineering and Technology (BUET), Dhaka, for his advice and inspiration to carry on my research.

Disclosure statement

No potential conflict of interest was reported by the authors.

ORCID

Ajoy Kumer 🕩: 0000-0001-5136-6166 Unesco Chakma 🕩: 0000-0003-1711-7216

References

- [1]M.N. Yoder, IEEE Trans. Electron Dev., 1996, 43, 1633–1636. [CrossRef], [Google Scholar], [Publisher]
- [2]Z. Wang, P.K. Nayak, J.A. Caraveo-Frescas, H.N. Alshareef, *Adv. Mater.*, **2016**, *28*, 3831-3892. [CrossRef], [Google Scholar], [Publisher]
- [3]M.J. Deen, F. Pascal, J. Mater. Sci.: Mater. Electron., 2006, 17, 549–575. [CrossRef], [Google Scholar], [Publisher]
- [4]C. Yuan, Y. Zhou, Y. Zhu, J. Liang, S. Wang, S. Peng, Y. Li, S. Cheng, M. Yang, J. Hu, B. Zhang, *Nat. Commun.*, **2020**, *11*, 3919. [CrossRef], [Google Scholar], [Publisher]
- [5]T. Hossain, M. Hossain, M. Ali, U. Chakma, A. Kumer, M.J. Islam, *Chem. Methodol.*, **2020**, *5*, 259–270. [CrossRef], [Google Scholar], [Publisher]
- [6] M.M. Alam, U. Chakma, A. Kumer, M.S. Islam, N.Z. Khandaker, T. Hossain, P. Chakma, J. Uddin, SPAST Abstracts, 2021, 1. [Google Scholar], [Publisher]
- [7]M. Suri, A. Hazarika, B.W. Larson, Q. Zhao, M. Vallés-Pelarda, T.D. Siegler, M.K. Abney, A.J. Ferguson, B.A. Korgel, J.M. Luther, *ACS Energy Lett.*, **2019**, *4*, 1954–1960. [CrossRef], [Google Scholar], [Publisher]
- [8]Y. Kim, J. Kim, H.M. Kim, J. Jang, Adv. Mater. Technol., 2020, 5, 1900857. [CrossRef], [Google Scholar], [Publisher]
- [9]X. Yuan, L. Meng, Z. Xu, C. Zheng, H. Zhao. *Environ. Sci. Technol.*, **2021**, *55*, 14080–14086. [CrossRef], [Google Scholar], [Publisher]
- [10] F. Wang, Y. Liu, Z. Ma, H. Li, Z. Kang, M. Shen, *New J. Chem.*, **2013**, *37*, 290–294. [CrossRef], [Google Scholar], [Publisher]
- [11] O.G. Gnonhoue, A. Velazquez-Salazar, É. David, I. Preda, *Polymers*, **2021**, *13*, 766. [CrossRef], [Google Scholar], [Publisher]

- [12] A. Balducci, J. Power Sources, 2016, 326, 534–540. [CrossRef], [Google Scholar], [Publisher]
- [13] S. Bhandari, B. Hao, K. Waters, C.H. Lee, J.C. Idrobo, D. Zhang, R. Pandey, Y.K. Yap, Acs Nano, 2019, 13, 4347–4353. [CrossRef], [Google Scholar], [Publisher]
- [14] I. Karabulut, S. Baskoutas, J. Appl. Phys., 2008, 103, 073512. [CrossRef], [Google Scholar], [Publisher]
- [15] S. Tomić, T. Sogabe, Y. Okada, Prog. Photovolt.: Res. Appl., 2015, 23, 546–558. [CrossRef], [Google Scholar], [Publisher]
- [16] A. Tyagi, K.M. Tripathi, N. Singh, S. Choudhary, R.K. Gupta, *RSC Adv.*, **2016**, *6*, 72423–72432. [CrossRef], [Google Scholar], [Publisher]
- [17] S. Mitra, S. Chandra, S.H. Pathan, N. Sikdar,
 P. Pramanik, A. Goswami, *RSC Adv.*, **2013**, *3*, 3189–3193. [CrossRef], [Google Scholar],
 [Publisher]
- [18] C. Ubani, M. Ibrahim, M. Teridi, K. Sopian, J. Ali, K. Chaudhary, *Solar Energy*, **2016**, *137*, 531–550. [CrossRef], [Google Scholar], [Publisher]
- [19] M.I. Ali, M.J. Islam, A. Kumer, M. Hossain, U. Chakma, D. Howlader, M. Islam, T. Hossain, *Materials Research*, **2021**, *24*. [Google Scholar], [Publisher]
- [20] D.H. Howlader, M. Sayed, U. Chakma, A. Kumer, M.J. Islam, M.T. Islam, T. Hossain, J. Islam, *Molecular Simulation*, **2021**, *44*, 1-12. [CrossRef], [Google Scholar], [Publisher]
- [21] S.Y. Lim, W. Shen, Z. Gao, *Chem. Soc. Rev.*, 2015, 44, 362–381. [CrossRef], [Google Scholar], [Publisher]
- [22] H. Sun, F. Zhang, H. Wei, B. Yang, J. Mater. Chem. B, 2013, 1, 6485–6494. [CrossRef], [Google Scholar], [Publisher]
- [23] U. Chakma, A. Kumer, K.B. Chakma, M.T. Islam, D. Howlader, M.J. Islam, M.K. Rasha;. *Eurasian Chem. Commun.*, **2020**, *2*, 573–580. [CrossRef], [Google Scholar], [Publisher]

- [24] U. Chakma, A. Kumer, B.K. Chakma, M.T. Islam, D. Howlader, *Adv. J. Chem. A*, **2020**, *3*, 542–550. [CrossRef], [Google Scholar], [Publisher]
- [25] M.M. Hasan, A. Kumer, U. Chakma, *Adv. J. Chem. A*, **2020**, *03*, 639–644. [CrossRef], [Google Scholar], [Publisher]
- [26] M.T. Islam, A. Kumer, D. Howlader, B.K. Chakma, U. Chakma, *Turkish Comput. Theor. Chem.*, **2020**, *4*, 24–31. [CrossRef], [Google Scholar], [Publisher]
- [27] B.K. Chakma, A. Kumer, U. Chakma, D. Howlader, M.T. Islam, *Int. J. New Chem.*, **2020**, 7, 247–255. [CrossRef], [Google Scholar], [Publisher]
- [28] M.J. Islam, A. Kumer, M.W. Khan, *Turkish Comput. Theor. Chem.*, **2020**, 5, 1–13. [CrossRef], [Google Scholar], [Publisher]
- [29] S. Mokit, U. Chakma, A. Kumer, M.J. Islam, A. Habib, M.M. Alam, *Appl. J. Environ. Eng. Sci.*, **2021**, *7*, 103-113. [CrossRef], [Google Scholar], [Publisher]
- [30] M.T. Islam, A. Kumer, U. Chakma, D. Howlader, Orbital: Electron. J. Chem., 2021, 13. [CrossRef], [Google Scholar], [Publisher]
- [31] A. Kumer, U. Chakma, Heliyon, 2021, 7, e07467. [CrossRef], [Google Scholar], [Publisher]
- [32] A. Mamun, A. Habib, U. Chakma, S. Mokit, A. Kumer, *Egypt. J. Chem.*, **2021**, 63. [CrossRef], [Google Scholar], [Publisher]
- [33] M.M. Hasan, A. Kumer, U. Chakma, M.T. Islam, *Molecular Simulation*, **2021**, *47*, 1-13. [CrossRef], [Google Scholar], [Publisher]
- [34] M.J. Islam, A. Kumer, *SN Appl. Sci.*, **2020**, *2*, 251. [CrossRef], [Google Scholar], [Publisher]
- [35] Perdew JPB, Kieron; Ernzerhof, Matthias, Phys. Rev. Lett., 1996, 77, 3865. [CrossRef], [Google Scholar], [Publisher]
- [36] J.M.G. del Campo, L. José, S.B. Trickey, Alberto Vela, J. Chem. Phys., 2012, 136, 104108. [CrossRef], [Google Scholar], [Publisher]

[37] M.M. Alam, U. Chakma, A. Kumer, M.S. Islam, N.Z. Khandaker, T. Hossain, P. Chakma, J. Uddin, SPAST Abstracts, 2021, 1. [Google Scholar], [Publisher] [38] Z.J. Yang K, Y. Zhao, D.G. Truhlar, *J. Chem. Phys.*, **2010**, *132*, 164117. [CrossRef], [Google Scholar], [Publisher]

HOW TO CITE THIS ARTICLE

Jahedul Islam, Ajoy Kumer*, Unesco Chakma*, Md. Monsur Alam, Shimul Biswas, Zubair Ahmad, Md. Shariful Islam, Ms. Ismat Jahan jony, Md Boshir Ahmed. Investigation of structural, electronic and optical properties of SrTiO₃ and SrTi_{0.94}Ag_{0.06}O₃ Quantum Dots based semiconductor Using First Principle Approach. *Adv. J. Chem. A*, **2022**, 5(2), 164-174.

DOI: 10.22034/AJCA.2022.325958.1300 URL: http://www.ajchem-a.com/article_147132.html

View publication stats